

TABRIZ PETROCHEMICAL COMPANY

GENERAL PURPOSE POLYSTYRENE - GPPS 1160

GPPS 1160 is a high-performance general purpose polystyrene engineered for demanding applications requiring high heat resistance and superior mechanical strength. This high molecular weight crystalline polymer is optimized for the extrusion and bi-oriented polystyrene (OPS) industries. Its robust nature makes it the premier choice for producing thick, durable sheets and high-quality thermoformed products.

Producer

Applications

Tabriz Petrochemical Company

Its versatility makes it essential for extruding thick sheets for insulation, creating high-clarity OPS films, and producing thermoformed goods like foam packaging and transparent household items.

Typical Properties

| Resin Properties | Unit | Typical Value | Test Method |
|--------------------------------------|---------|---------------|---------------|
| MELT FLOW INDEX (200°C-5KG) | g/10min | 2.5 | ASTM D-1238 |
| STYRENE RESIDUAL MONOMER | PPM | <500 | CLG LABPSG004 |
| VICAT SOFTENING POINT (50 °C/hr 1kg) | °C | 103 | ASTM D-1525 |
| HDT(120°C/HR AND 1.82MPa) | °C | 84 | ASTM D-648 |
| TENSILE STRENGTH AT BREAK | MPa | 52 | ASTM D-638 |
| ELONGATION AT BREAK | % | 3 | ASTM D-638 |
| TENSILE MODULUS | MPa | 4300 | ASTM D-638 |
| FLEXURAL MODULUS | MPa | 3100 | ASTM D-790 |
| FLEXURAL STRENGTH | МРа | 90 | ASTM D-790 |
| IZOD IMPACT(NOTCHED) | Kj/m2 | 2.0 | ISO180/1A |
| ROCKWELL HARDNESS | - | M SCALE/ 72 | ASTM D-785 |
| HAZE | % | 1 | ASTM D-1003 |
| DENSITY | gr/cm3 | 1.04 | ASTM D-792 |
| SHRINKAGE | % | 0.55 | ASTM D-955 |